



**A. LACROIX GRANIT**  
GENERATIONS OF KNOW-HOW

450, RUE PRINCIPALE  
SAINT-SÉBASTIEN (QUÉBEC) G0Y 1M0  
TEL: 819-652-2828 - FAX: 819-652-2098  
WWW.LACROIXGRANITE.COM

## ATLANTIC BLACK

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,06%
<b>ASTM C97</b>	Density	184,8 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	26 472 psi
<b>ASTM C99</b>	Modulus of rupture	2 255 psi
<b>ASTM C880</b>	Flexural strength	1 741 psi

## ORION

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,045 %
<b>ASTM C97</b>	Density	170.1 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	26 592.5 psi
<b>ASTM C99</b>	Modulus of rupture	2174.25 psi

## CRYSTAL BLACK

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0.04 %
<b>ASTM C97</b>	Density	172.9 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	20 957.5 psi
<b>ASTM C99</b>	Modulus of rupture	1903.5 psi
<b>ASTM C880</b>	Flexural strength	1563.5 psi

## SPRING GREEN

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,12 %
<b>ASTM C97</b>	Density	173,5 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	27 472 psi
<b>ASTM C99</b>	Modulus of rupture	1 646 psi
<b>ASTM C880</b>	Flexural strength	1 399 psi

## ATLANTIC GREEN

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,12 %
<b>ASTM C97</b>	Density	168,7 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	24 081 psi
<b>ASTM C99</b>	Modulus of rupture	1 515 psi
<b>ASTM C880</b>	Flexural strength	1 341 psi

## ATLANTIC BLUE

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,06 %
<b>ASTM C97</b>	Density	171,8 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	25 221 psi
<b>ASTM C99</b>	Modulus of rupture	1 668 psi
<b>ASTM C880</b>	Flexural strength	1 542 psi

## AUTUMN HARMONY

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,13 %
<b>ASTM C97</b>	Density	168,4 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	23 168 psi
<b>ASTM C99</b>	Modulus of rupture	1 615 psi
<b>ASTM C880</b>	Flexural strength	1 442 psi



**A. LACROIX GRANIT**  
GENERATIONS OF KNOW-HOW

450, RUE PRINCIPALE  
SAINT-SÉBASTIEN (QUÉBEC) G0Y 1M0  
TEL: 819-652-2828 - FAX: 819-652-2098  
WWW.LACROIXGRANITE.COM

## AUTUMN BROWN

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,10 %
<b>ASTM C97</b>	Density	170 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	23 690 psi
<b>ASTM C99</b>	Modulus of rupture	1 741 psi
<b>ASTM C880</b>	Flexural strength	1 504 psi

## DEER BROWN

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,137 %
<b>ASTM C97</b>	Density	169,2 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	26 419 psi
<b>ASTM C99</b>	Modulus of rupture	1 515 psi
<b>ASTM C880</b>	Flexural strength	1 413 psi

## CHAMBORD

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,06 %
<b>ASTM C97</b>	Density	168.8 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	23 046.8 psi
<b>ASTM C99</b>	Modulus of rupture	1 662.3 psi

Autres granits disponibles

## NORDIC RED

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,28 %
<b>ASTM C97</b>	Density	165,2 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	29 336 psi
<b>ASTM C99</b>	Modulus of rupture	1 706 psi
<b>ASTM C880</b>	Flexural strength	1 719 psi

## ATLANTIC PINK

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,189 %
<b>ASTM C97</b>	Density	167,3 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	26 487,5 psi
<b>ASTM C99</b>	Modulus of rupture	1 575 psi

## NEW RAINBOW

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,094 %
<b>ASTM C97</b>	Density	165,7 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	38 147 psi
<b>ASTM C99</b>	Modulus of rupture	2 300 psi
<b>ASTM C880</b>	Flexural strength	1 957,5 psi

## ST-SÉBASTIEN GREY

Country of origin: Canada

<b>ASTM C97</b>	Absorption by weight	0,28 %
<b>ASTM C97</b>	Density	165.2 lb /pi <sup>3</sup>
<b>ASTM C170</b>	Compressive strength	29 336.25 psi
<b>ASTM C99</b>	Modulus of rupture	1 705.75 psi